


Oxidal Oberflächen



Importeur Schweiz:
Starakustik.com
Schuler Modul AG
Gitschenstrasse 10
CH-6460 Altdorf

Tel: 041 878 11 92
info@star-akustik.ch



SPECIFICATIONS	DESCRIPTION	
Coating	FEVE (Fluoro Ethylene and Vinyl Ether)	
Thickness	14± 2 µm	According to EN 13523-1
Gloss	Low, semi, high gloss	According to EN 13523-2 20 - > 90 gloss units
Gloss tolerance	± 5 U, High gloss : > 90	According to EN 13523-2
Colour	High colour reproducibility	Visual adjustment
Bending properties	Excellent bending properties	According to EN 13523-7 No cracking at T1.5
UV resistance	20 years warranty	RUV4 according to table C.3 2 000h UVA: Close to 100% gloss retention
Corrosion resistance	High corrosion resistance	According to EN 1396, C.6.5 Acetic acid salt spray fog resistance, index 2 according to table C.5.